

Graphic Marble

Tuft gauge	1/10 loop pile	ISO 2424
Pilecomposition	100% PA SDN	ISO 2424
Primary Backing	Non Woven	ISO 2424
Secondary backing	Bitumen	ISO 2424
Width	50x50 cm ± 0,2%	EN 984
Pile Density	0.126 gr/cm ³	ISO 8543
Pile Weight	770 gr/m ²	ISO 8543
Total weight	Bitumen : 4525 gr/m ² ± 15%	ISO 8543
Pile height	3 mm ± 2 mm	ISO 1766
Total Height	Bitumen : 6 mm	ISO 1765
Number of knots	240.379 /m ² -7.5% .+10%	ISO 1763
Fire Classification	Bfl-S1	EN 13501-1
Transversal resistance	Ω	ISO 10965
Use Area	Heavy project use (33)	EN 1307
GUT Nr.	E9A5EFE3	www.pro-dis.info
Sound Absorption	125 Hz 250 Hz 500 Hz 1000 Hz 2000 Hz 4000 Hz 0,00 0,05 0,05 0,20 0,30 0,35	ISO 11654
Evaluated sound absorptions grade	0,15 αW αW	
Sound Insulation	25 dB	ISO 10140
Thermal resistance	0,0639 (0,639 TOG) M ² KW	ISO 8302
Light fastness	≥ 5	105-B02
Wearebility	≥ 4	105-X12
Water fastness	≥ 4	105-E01
Electrostatic charging	<2 kV	ISO 6356
Luxury class	LC3	EN 1307
Pictures	www.condorcontract.com	

Floorsymbols



Certificates

