

CE DECLARATION OF PERFORMANCE

according to Regulation (EU) No. 305 of the European Parliament and the Council of 9 March 2011

DOP no.

DOP-734-00

1 Unique product identification code:

734 (recipe no.)
6 to 40 mm (panel thickness)

2 Use:

Structural or load-bearing components for indoor use
in dry and humid conditions

3 Name and Manufacturer

Registered trade name or registered brand and
contact address of the manufacturer:

EGGER OSB 3 E0
EGGER Ergo Board

EGGER Holzwerkstoffe Wismar GmbH & Co KG
Am Haffeld 1
D-23970 Wismar
web: www.egger.com

4 not applicable

5 System for the assessment and verification
of constancy of performance of the building product:

System 2+

6 Harmonized standard

EN 13986:2004+A1:2015

Notified body:

no. 0765

Wilhelm-Klauditz-Institut (WKI)
Bienroder Weg 54 e
D-38108 Braunschweig

7 Declared performance:

Specification			Panel thickness [mm]						
		unit	> 6 - 10	> 10 - <18	18 - 25	> 25 - 32	>32 - 40		
Bending strength	bending acc. to EN 310 - 0° major axis o°	N/mm²	≥ 22	≥ 20	≥ 18	≥ 16	≥ 14	technical class OSB/3 acc. to EN 300	
	bending acc. to EN 310 – 90° minor axis	N/mm²	≥ 11	≥ 10	≥ 9	≥ 8	≥ 7		
Modulus of Elasticity	bending acc. to EN 310 - 0° major axis o°	N/mm²	≥ 4000	≥ 4000	≥ 4000	≥ 3500	≥ 3500		
	bending acc. to EN 310– 90° minor axis	N/mm²	≥ 1400	≥ 1400	≥ 1400	≥ 1400	≥ 1400		
Essential characteristics			Panel thickness [mm]						Harmonized technical specification
		unit	> 6 - 10	> 10 - <18	18 - 25	> 25 - 32	>32 - 40		
Durability	thickness swelling 24h	%	≤ 15					EN 13986:2004+A1:2015	
	Internal bond	N/mm²	≥ 0.34	≥ 0.32	≥ 0.30	≥ 0.29	≥ 0.26		
	internal bond - option 1	N/mm²	≥ 0.18	≥ 0.15	≥ 0.13	≥0.10	≥0.08		
	bending strength - major axis - option 1 mechanical	N/mm²	≥ 9	≥ 8	≥7	≥6	≥6		
		k _{def}	k _{mod permanent}	k _{mod long}	k _{mod medium}	k _{mod short}	k _{mod instantenous}		
	SC1	1.50	0.40	0.50	0.70	0.90	1.10		
	SC2	2.25	0.30	0.40	0.55	0.70	0.90		
biological (use class)			GK 1 & 2						
Release of Formaldehyde	acc. to EN 717-1	ppm	< 0.03 (no added formaldehyde) Emission class E1						
Release of PCP		ppm	< 3.0						
Density		kg/m³	≥ 600 kg/m³						
Water vapour permeability	µ (dry / wet)	-	200 / 150						
Thermal conductivity		W/mK	0.13						
Airborne sound insulation	sound absorption coefficient	-	0.10 / 0.25 (frequency range 250 - 500 Hz / 1000-2000 Hz)						
	sound insulation R	dB	R = 14 * lg(m _A) + 13 (area mass related m _A , frequency range 1 to 3 kHz)						
Air permeability	acc. to EN 12114 (at 50Pa pressure difference)	m/(m² * h)	NPD						
Reaction to fire *)		class	class floor covering		Minimum thickness [mm]				
	without air gap behind OSB _{a,b,e,f}	D-s2, d0	D _{fl,s1}		9 mm				
	with closed air gap or open air gap ≤ 22mm behind OSB _{c,e,f}	D-s2, d0	-		9 mm				
	with closed air gap behind OSB _{d,e,f}	D-s2, d0	D _{fl,s1}		15 mm				
	with open air gap behind OSB _{d,e,f}	D-s2, d0	D _{fl,s1}		18 mm				
	without restriction _{e,f}	E	E _{fl}		3 mm				

Essential characteristics		unit	panel thickness [mm]					Harmonized technical specification
			> 6 - 10	> 10 - <18	18 - 25	> 25 - 32	>32 - 40	
Characteristic strength								EN 13986:2004+A1:2015
Bending f_m	0° - major axis	N/mm²	18.0	16.4	14.8	NPD	NPD	
	90° - minor axis	N/mm²	9.0	8.2	7.4	NPD	NPD	
Tension f_t	0° - major axis	N/mm²	9.9	9.4	9.0	NPD	NPD	
Compression f_c	90° - minor axis	N/mm²	7.2	7.0	6.8	NPD	NPD	
	0° - major axis	N/mm²	15.9	15.4	14.8	NPD	NPD	
Shear $f_v \perp$ panel surface	90° - minor axis	N/mm²	12.9	12.7	12.4	NPD	NPD	
	0° - major axis / 90° - minor axis	N/mm²	6.8	6.8	6.8	NPD	NPD	
Shear f_r in panel surface	0° - major axis / 90° - minor axis	N/mm²	1.0	1.0	1.0	NPD	NPD	
Mean stiffness								
Bending E_m	0° - major axis	N/mm²	4930	4930	4930	NPD	NPD	
	90° - minor axis	N/mm²	1980	1980	1980	NPD	NPD	
Tension E_t	0° - major axis	N/mm²	3800	3800	3800	NPD	NPD	
	90° - minor axis	N/mm²	3000	3000	3000	NPD	NPD	
Compression E_c	0° - major axis	N/mm²	3800	3800	3800	NPD	NPD	
	90° - minor axis	N/mm²	3000	3000	3000	NPD	NPD	
Shear $G_v \perp$ panel surface	0° - major axis / 90° - minor axis	N/mm²	1080	1080	1080	NPD	NPD	
Shear G_r in in panel surface	0° - major axis / 90° - minor axis	N/mm²	50	50	50	NPD	NPD	
Impact resistance		N/mm²	NPD	NPD	NPD	NPD	NPD	
Embedding strength		N/mm²	EN 1995-1-1, Abs. 8					
Racking resistance		N/mm²	EN 1995-1-1					
Performance wall EN 12871	soft body impact acc. to EN 596	-	Pass					
	panel thickness	mm	≥ 9 mm					
	EGGER Ergo Board acc. to DIN 4103-1	mm	≥ 12 mm installation class 1 and 2					
Performance Floor EN 12871 (major axis. 0°)	load category	-		A	A			
	panel thickness	mm		≥ 15	≥ 18			
	cc-span	mm		≤ 410	≤ 625			
Performance roof EN 12871 (major axis. 0°)	load category	-		H	H			
	panel thickness	mm		≥ 12	≥ 18			
	cc-span	mm		≤ 625	≤ 833			

8 not applicable

The product performance according to number 1 corresponds to the declared performance according to number 7. Solely the manufacturer is responsible for drafting the declaration of performance according to number 3.

Signed for and in the name of the manufacturer by:



Thomas Schlund

EGGER Building Products - Head of Division
Technology/Production

Wismar, 18.10.2016

*) Note:

- a Without air gap installed directly on products in classes A1 or A2-s1, d0 with a minimum raw density of 10 kg/m³ or at least products of class D-s2,d2 with a minimum raw density of 400 kg/m³.
- b An underlayment made of cellulose thermal insulation material of at least class E may be used if installed directly behind the wood-based material; however, this does not apply to flooring.
- c Installed with air gap behind, the product bordering with its rear side the empty space must correspond at least to class A2-s1,d0 with a minimum raw density of 10 kg/m³.
- d Installed with air gap behind, the product bordering with its rear side the empty space must correspond at least to class D-s2,d2 with a minimum raw density of 400 kg/m³.
- e With the exception of flooring, the class also corresponds to veneered, phenol and melamine-faced boards.
- f A vapour barrier with a thickness of up to 0.4 mm and a mass of up to 200 g/m² may be installed between the wood-based material and the underlayment if there is no air gap in between.